

MFS 1140

AQUEOUS DEVELOPER

INTRODUCTION

MFS 1140 Aqueous Developer is ideal for the development of aqueous dry films and liquid photo-imageable soldermask systems.

BENEFITS

Liquid concentrate – eliminates handling and storage of dry powders

Does not contain toxic glycol ethers

Consistent performance

Instant mixing – no waiting for powders to dissolve

SOLUTION MAKE-UP

MFS 1140 Aqueous Developer

2.5% v/v with water

OPERATING DATA

Concentration	2-3%
pH	10.4-11.5
Temperature	25 - 40 deg C.
Filtration	Continuous in line
Extraction	Recommended.

EQUIPMENT

Tanks	Polypropylene, unplasticised PVC, Stainless Steel, titanium, hastelloy
Heaters	PTFE, Teflon coated or stainless steel immersion heaters with thermostatic control
Filtration	Continuous in line

INSTALLATION

It is essential that the tanks to be used for MFS 1140 Aqueous Developer are thoroughly cleaned and leached before any product is introduced.

If in any doubt as to the cleaning procedure please contact PMD (UK) Limited Technical Department.

1. Fill the clean empty tank with the required volume of water.
2. Add the required volume of MF 1140 Aqueous Developer and mix thoroughly.
3. Heat to operating temperature.

MAINTENANCE AND CONTROL

Evaporation losses should be replaced with water.

Maintain at pH 11 by additions of MFS 1140 Aqueous developer.

When developing time becomes excessive or pH is not maintained above 10.4, the solution should be discarded and a new one prepared.

As a guide 1lt of solution will process approximately 0.3m² of resist.

ANALYSIS METHOD

MFS 1140 Aqueous Developer Concentration

Reagents

0.1N Hydrochloric Acid (standard volumetric solution).
Methyl Orange Indicator.

Method

1. Pipette a 10 ml sample of the working solution into a 250 ml flask.
2. Add approximately 100 mls of water and mix thoroughly.
3. Add a few drops of methyl orange indicator.
4. Titrate with 0.1N Hydrochloric Acid to the first orange end point.
5. Record titre = t mls.

Calculation

$t \times 0.173 = \text{concentration (\%)} \text{ MFS 1140.}$

Replenishment

To increase the concentration by 0.5% add 5 ml per litre of the MFS 1140.

NOTES

During use dissolved photo polymers will cause the bath to foam. MFS 1402 Anti-foam should be added initially at 1-3ml/L then in 0.25ml/L increments as required to control the foam.

DISPOSAL

Dispose of in accordance with local authority requirements.

PRODUCT FAMILIES

The following products are referred to in this data sheet.

<u>Product Name</u>	<u>Product Number</u>
MFS 1140 Aqueous Developer	945048
MFS 1402 Anti-foam	964031

Whilst every endeavour has been made to ensure that the information given in this data sheet is correct, PMD (UK) gives no warranty, express or implied, relating to the use or performance of this product.